

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
28 December 2000 (28.12.2000)

PCT

(10) International Publication Number
WO 00/78688 A1

(51) International Patent Classification⁷: **C04B 28/02 //**
(C04B 28/02, 22:06, 22:14, 24:04, 24:12), 103:10

(74) Agent: MCSTEA, John, Anthony; MBT (Schweiz) AG,
Patents and Trade Marks, Vulkanstrasse 110, CH-8048
Zürich (CH).

(21) International Application Number: PCT/EP00/04909

(81) Designated States (*national*): JP, NO, US.

(22) International Filing Date: 29 May 2000 (29.05.2000)

(84) Designated States (*regional*): European patent (AT, BE,
CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC,
NL, PT, SE).

(25) Filing Language: English

(26) Publication Language: English

Published:

— *With international search report.*


(30) Priority Data:
99201963.8 18 June 1999 (18.06.1999) EP

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(71) Applicant (*for all designated States except US*): MBT
HOLDING AG [CH/CH]; Vulkanstrasse 110, CH-8048
Zürich (CH).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): HOFMANN, Thomas
[CH/CH]; Dorfstrasse 22, CH-8166 Niederweningen (CH).



WO 00/78688 A1

(54) Title: CONCRETE ADMIXTURE

(57) Abstract: An accelerating admixture for sprayed concrete comprises: (a) the reaction product of aluminium hydroxide with an organic acid; (b) aluminium sulphate; and (c) at least one alkanolamine. Concrete to which accelerator has been added sets rapidly.

Concrete Admixture

This invention relates to cementitious compositions and to accelerating admixtures for use therein, especially as shotcrete accelerators.

5

Sprayed concrete or "shotcrete", which is applied to substrates such as rock faces and tunnels by spraying must set very rapidly. In such a use, the traditional concrete accelerators such as calcium chloride are not effective, and more powerful accelerators must be used, including sodium aluminate and alkali metal hydroxides. These are highly alkaline, which gives rise both to handling difficulties and unpleasant conditions when spraying in confined spaces such as tunnels.

10

An alternative accelerating technology based on aluminium compounds has been known for some time. The use of aluminium hydroxide either alone or combined with other materials is described in, for example, Japanese Kokai S51-144425 and European Patent 0 076 927.

15

In a variation on this, aluminium hydroxide may be partially reacted with an acid, preferably an organic acid - see, for example GDR Patent DD 226 344, British Patent GB2 307 475 and European Application 0 798 300.

20

Aluminium sulphate is also known as a component of accelerating systems, and is described in, for example, Japanese Kokais S50-143816, S58-99147 and S63-291839, and European Patent Application 0 812 812. Another aluminium compound which has been used in concrete accelerators is basic aluminium sulphate (also known as aluminium hydroxysulphate) - see, for example, European Patents 0 711 260 and 0 775 097.

25

It has now been found that a particularly effective accelerating admixture can be prepared by a combination of particular components. There is therefore provided, according to the present invention, an accelerating admixture for sprayed concrete, comprising

30

- (a) the reaction product of aluminium hydroxide with an organic acid;
- (b) aluminium sulphate; and
- (c) at least one alkanolamine.

5 Reaction products of aluminium hydroxide and organic acids are known to the art, and are described in, for example, the abovementioned DD 226 344 and GB 2 307 475. The products have the formula $\text{Al}(\text{OH})_{3-x}\text{R}_x$, where R is an anion of an organic acid. The acid is preferably a carboxylic acid, more preferably a lower (C_1 - C_6) alkanolic acid and most preferably either formic acid or acetic acid, most preferably formic acid. The value
10 of x can vary across a wide range, as is disclosed in these patents, and the same values apply in this invention.

Aluminium sulphate is a well-known and readily-available raw material and any of the commercial grades are suitable for use in this invention, for example the so-called
15 "12%" and "17%" grades (referring to the theoretical weight percentage of aluminium oxide present).

The alkanolamine for use in this invention may be selected from any such material known to the art. The preferred alkanolamines are diethanolamine, triethanolamine and
20 methyldiethanolamine. A mixture of two or more such materials may be used.

The weight proportions of the components which are combined to form the accelerating admixtures according to the invention are

25	<u>component</u>	<u>widest range</u>	<u>preferred range</u>
	formic acid	1-10	6-8
	aluminium hydroxide	1-30	16-18
	aluminium sulphate	30-60	35-55
	alkanolamine	0.1-12	0.5-8.0

the remainder to 100% being water. The preferred formic acid is quoted here, but the same ranges apply to the other C1-C6 alkanolic acids.

5 With regard to the alkanolamines, the "widest range" given corresponds to the extremes of the different alkanolamines. The proportions of the various alkanolamines vary substantially. For example, the actual "widest ranges" for the three preferred materials are

diethanolamine	1-12%
triethanolamine	0.1-4%
10 methyldiethanolamine	1-8%

However, the skilled person can readily ascertain what works and the "preferred range" is valid for all alkanolamines.

15 In an especially preferred embodiment of the invention, the admixture may additionally contain ferric sulphate, to the extent of from 0.1-1.0% by weight of cement. The addition of this material produces a noticeable improvement in performance.

20 The admixture according to the invention may be manufactured by any convenient means. The order of addition of components is not critical. Thus, for example, it is possible and permissible first to react the formic acid and the aluminium hydroxide to form products of the type described in the abovementioned DD 226 344, and then to add the other components thereto. The reaction is carried out at elevated temperature, no higher than 90°-95°C. Alternatively, the aluminium hydroxide may be added last, to a
25 heated mixture of the other components. This is a preferred method.

The admixture of the present invention may be used in an art-recognised manner with shotcrete. The invention therefore provides a process of coating a substrate with concrete by preparing a sprayable concrete mix and spraying this mix on to the substrate
30 through a nozzle, there being supplied to the mix at the nozzle an accelerating admixture as hereinabove described. The admixture is provided to the nozzle as an aqueous solution

or suspension at typically 50-60% solids by weight of the suspension, and so that the concrete receives from 0.5 to 15% by weight of admixture (solids on cement). The actual figure used will vary, depending on the type of cement and the mix design, but the provision of a suitable quantity is well within the skill of the art.

5

The invention therefore additionally provides a method of applying a layer of concrete to a substrate by spraying it through a nozzle, wherein there is added at the nozzle an accelerating amount of an accelerating admixture as hereinabove described.

10 The admixtures of the invention bring about unusually fast setting in comparison with other known alkali-free accelerators.

The invention further provides a layer of hardened concrete applied by spraying to a substrate via a nozzle, hardening having been accelerated by the addition at the nozzle
15 of an accelerating amount of an accelerating admixture as hereinabove described.

The invention is now illustrated with reference to the following non-limiting examples in which all parts are expressed by weight.

20 Preparation of accelerating admixture according to the invention

The composition is as follows

	water	26 parts
	formic acid	8 "
25	aluminium hydroxide	18 "
	aluminium sulphate (17% grade)	42 "
	diethanolamine (DEA)	6 "

Water, formic acid and aluminium sulphate are mixed and heated to 50°C. At this
30 point, DEA is added slowly with stirring. This is followed by the addition of aluminium

hydroxide, again with stirring. Stirring is continued and the temperature is raised to 85°C and held there until a clear liquid is formed.

The accelerating admixture thus prepared is tested in cement paste and mortar against two high-performance commercially-available alkali-free accelerators.

5

Two different types of Portland cement are used, Siggenthal Normo 4 CEM I 42.5 (hereinafter "Type A") and Schwenk CEM I 42.5 (hereinafter "Type B").

Mortar test

10 The mortar was made according to the European Standard EN 196-1 formulation, that is

	cement	450 parts
	sand	1350 "
15	water	189 "

this giving a water/cement (w/c) ratio of 0.42.

20 To samples of the mortar composition are added the accelerating admixture prepared as hereinabove described (hereinafter "Type I") and two commercial alkali-free accelerators, these being

- MEYCO (trade mark) SA 160 ex MBT (Schweiz) AG, Switzerland (hereinafter "Type II")
- 25 - F100 ex Giulini Chemie GmbH, Germany (hereinafter "Type III")

These are used in a concentration of 5% (solids by weight of cement). There is additionally added 1.5% (weight solids on cement) of "Rheobuild" (trade mark) 1000 ex MBT (Schweiz) AG, a BNS-type water reducer. In this form the mortar has a flow of

30 17 cm as measured by German Industrial Standard DIN 18555.

The mortar is subjected to a setting test using Vicat needles according to European Standard EN 196, part 3. The results are shown in the following table.

	<u>Cement type</u>	<u>Accelerator type</u>		
		I	II	III
Initial setting (min)	Type A	1	9.5	2
	Type B	0.5	3	0.5
Time to 1 mm penetration (min)	Type A	3	18	6.5
	Type B	2	17	2
Final setting (min)	Type A	4.5	30	13
	Type B	2.5	20	3

- 5 The admixture according to the invention performs better than both accelerators.

Paste test

The pastes have a w/c ratio of 0.27 and samples are dosed with 5% (solids on cement) of accelerators. The pastes additionally contain 1% (solids on cement)

- 10 "Rheobuild" 1000.

The setting of the pastes is tested as per the mortar samples, and the results are shown in the following table.

	<u>Cement type</u>	<u>Accelerator type</u>		
		I	II	III
Initial setting (min)	Type A	2	4	12
	Type B	0.5	4	3
Final setting (min)	Type A	17	17	17
	Type B	3	16	13

Again, it can be seen that the overall performance of the accelerating admixture according to the invention is appreciably superior to the commercially-acceptable compositions.

Claims:

1. An accelerating admixture for sprayed concrete, comprising
 - (a) the reaction product of aluminium hydroxide with an organic acid;
 - 5 (b) aluminium sulphate; and
 - (c) at least one alkanolamine.
2. An accelerating admixture according to claim 1, wherein the acid is a C_1 - C_6 alkanolic acid, preferably formic or acetic acid, most preferably formic acid.
- 10 3. An accelerating admixture according to claim 1 or claim 2, wherein the alkanolamine is at least one of diethanolamine, triethanolamine and methyldiethanolamine.
- 15 4. An accelerating admixture according to any one of claims 1-3, wherein the admixture has the following composition, given as percentages by weight:

formic acid	1-10
aluminium hydroxide	1-30
20 aluminium sulphate	35-55
alkanolamine	0.5-0.8
water	to 100%
5. A method of preparing an accelerating admixture for use with sprayed concrete,
 - 25 comprising the addition of alkanolamine, aluminium sulphate and organic acid to water,
 - heating and then adding aluminium hydroxide.
6. A process of coating a substrate with concrete by preparing a sprayable concrete mix and spraying this mix on to the substrate through a nozzle, there being supplied to
30 the mix at the nozzle an accelerating admixture according to any one of claims 1-4.

7. A method of applying a layer of concrete to a substrate by spraying it through a nozzle, wherein there is added at the nozzle an accelerating amount of an accelerating admixture according to any one of claims 1-4.
- 5 8. A layer of hardened concrete applied by spraying to a substrate via a nozzle, hardening having been accelerated by the addition at the nozzle of an accelerating amount of an accelerating admixture according to any one of claims 1-4.

INTERNATIONAL SEARCH REPORT

In ational Application No

PCT/EP 00/04909

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C04B28/02 //(C04B28/02,22:06,22:14,24:04,24:12),C04B103:10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP 0 812 812 A (MBT HOLDING AG) 17 December 1997 (1997-12-17) cited in the application claim 1; example 1 ---	1-3,6-8
Y	DD 266 344 A (NORDHAUSEN SCHACHTBAU) 29 March 1989 (1989-03-29) cited in the application claims 1,3 ---	1-3,6-8
A	GB 2 307 475 A (SANDOZ LTD) 28 May 1997 (1997-05-28) cited in the application page 2, line 6-11; claims 1,4,7 --- -/--	1,2,6-8

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

6 September 2000

Date of mailing of the international search report

13/09/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040. Tx. 31 651 eponl.

Authorized officer

Naaloman P

INTERNATIONAL SEARCH REPORT

In ational Application No

PCT/EP 00/04909

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 96 05150 A (SANDOZ LTD ;SANDOZ AG (DE); SANDOZ AG (AT); LEIKAUF BERNHARD (CH)) 22 February 1996 (1996-02-22) cited in the application claims 1,4 ----	1
A	WO 98 18740 A (LUNKENHEIMER RUDOLF ;SEDELIES REINHOLD (DE); ALTMANN HORST (DE); B). 7 May 1998 (1998-05-07) claims 1,4 ----	1
A	FR 2 031 950 A (DUFRETHI) 20 November 1970 (1970-11-20) -----	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 00/04909

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0812812	A	17-12-1997	AU 2369697 A BR 9703581 A CN 1171378 A JP 10087358 A NO 972740 A US 5935318 A	18-12-1997 22-09-1998 28-01-1998 07-04-1998 15-12-1997 10-08-1999
DD 266344	A	29-03-1989	NONE	
GB 2307475	A	28-05-1997	AT 403276 B AT 203796 A DE 19647018 A FR 2741616 A IT RM960800 A JP 9165246 A US 5772753 A	29-12-1997 15-05-1997 28-05-1997 30-05-1997 22-05-1998 24-06-1997 30-06-1998
WO 9605150	A	22-02-1996	AT 174887 T AU 701619 B AU 3257895 A DE 69506881 D DE 69506881 T EP 0775097 A ES 2125644 T FI 970551 A JP 10504273 T US 5968256 A	15-01-1999 04-02-1999 07-03-1996 04-02-1999 02-06-1999 28-05-1997 01-03-1999 07-02-1997 28-04-1998 19-10-1999
WO 9818740	A	07-05-1998	CZ 9901399 A EP 0946451 A FI 990920 A NO 991769 A PL 332831 A SK 51599 A	17-11-1999 06-10-1999 23-04-1999 14-04-1999 11-10-1999 10-12-1999
FR 2031950	A	20-11-1970	NONE	

THIS PAGE BLANK (USPTO)